

MATRIX X1 LUX AA

PARLAK SYNTHETIC GLOSSY PAINT

MATRİX X1 LUX AA

SENTETİK PARLAK BOYA

Revizyon Tarihi: 01.11.2008

Product Description:

Alkyd based glossy synthetic topcoat. It is unleaded paints.

Properties:

X1 is applicable indoors and outdoors wooden, metal and plaster surface and It is used for land and marine vehicles. X1 has high gloss and hiding power, good adhesion and perfect working properties. It is unleaded paints. It resists to yellowish.

Specifications:

Color: Consult color catalogue.

Gloss (60°): min. 90

Solid, % (weight): 72 ± 2

Density (g/cm³, 20°C): 1.20 ± 0.02

Viscosity (KU, 25°C): 95 ± 2

Flash point: >38 °C

Applications:

Coverage: Approximately 15-20 m²/L. for single coat.

Drying Time (20°C): Set to touch drying within 2-3 hours, dust free drying within 5-6 hours and hard drying within 18 hours.

Recommended Application:

a) Surface preparation: Old paints and dust on the surface should be removed. Politex Decorative or Polistar Synthetic Primer or X1 Synthetic Lux Primer should be applied as a primer for wooden and plaster surfaces. For metal surface dirt, grease and oils should be cleaned. Antipas Antirust Primer should be applied to the metal surface as a primer.

b) Application: It is recommended to apply 2 coats. At least 1 day should be allowed between coats.

c) Tools: Brush, roller or spray.

d) Thinned Ratio: 15-20 % with Polisan Synthetic Thinner.

Storage Conditions :

Store in closed packages at cool place.

Standart Package :

0.250 L. ,0.7 L, 2.5 L, 3.75 L, 7.5 lt,15 L

Ürün Tanımı :

Alkid bağlayıcı esaslı, üstün özellikleri olan parlak son kat bir boyadır. Kurşun içermez.

Özellikleri:

İç ve dış mekanlardaki ahşap, sıva ve metal yüzeylerde, kara ve deniz araçlarında kullanılır. Yüksek parlaklığa ve örtücülüğe sahiptir. Parlaklığı kalıcıdır. Uygulama kolaylığı ve iyi yayılma özelliği ile düzgün yüzeylerin oluşmasını sağlayan, üstün kaliteli son kat boyadır. Kurşunsuzdur. Sararmaya karşı direnci yüksektir.

Spesifikasyonlar:

Renk : Renk kataloguna bakınız.

Parlaklık (60°) : min. 90

Katı, % (weight) : 72 ± 2

Yoğunluk (g/cm³, 20°C) : 1.20 ± 0.02

Viskozite (KU, 25°C) : 95±2

Parlama Noktası: > 38 °C

Uygulama :

Boyanabilen Alan : Tek katta yaklaşık 15-20 m² /L

Kuruma Zamanı (20 °C): Dokunma kurumasını 2-3 saatte; toz tutmama kurumasını 5-6 saatte; sert kurumasını 18 saatte tamamlar.

Tatbikat :

a) Yüzey Hazırlama : Budakları yakılıp, varsa eski boya kazınan, zımparalanıp, tercihen renksiz POLİTEX DEKORATİF AHŞAP KORUYUCU ile doyurulan ahşap yüzeyler ile sıvalı yüzeyler POLİSTAR SENTETİK ASTAR veya X1 LUX SENTETİK ASTAR ile; metal yüzeyler ise kir, pas ve yağları temizledikten sonra POLİSAN ANTİPAS ile astarlanmalıdır.

b) Tatbikat Şekli : İki kat olarak uygulanır. İkinci kat uygulanmadan önce 1 gün beklenmelidir.

c) Kullanılan Aletler : Fırça, rulo veya boya tabancası.

d) İnceltme/Karışım Oranı : POLİSAN SENTETİK TİNER ile % 15-20 oranında inceltilir.

Depolama Koşulları :

Ağzı kapalı ambalajlarda, serin yerde depolayınız.

Ambalaj Bilgisi :

0.250 L. ,0.7 L, 2.5 L, 3.75 L, 7.5 lt,15 L

Remarks:

R10 :Flammable

R20/21/22 :Harmfull by inhalation , in contact with skin and if swallowed.

S2: Keep out of reach of children

S16: Keep away from sources of ignition - No Smoking.

S24/25: Avoid contact with skin and eyes.

S46 : If swallowed , seek medical advice immediately and show this container or label.

S51 : Use only in well- ventilated areas.

It confirms with TS 39 and certificated TSE standart.

Uyarılar

R10 : Alevlenebilir.

R20/21/22: Solunduğunda, yutulduğunda ve deri ile temasta sağlığa zararlıdır.

S2: Çocukların erişemeyeceği yerde muhafaza ediniz.

S16: Tutuşturma kaynaklarından uzak tutunuz.

SİGARA İÇİLMEZ

S24/25: Göz ve deri ile temasından sakınınız.

S46: Yutulduğunda derhal doktora danışınız; kabı veya etiketi gösteriniz

S51: Sadece iyi havalandırılan yerlerde kullanınız.

POZ NO : 04.505

TS 39 ‘a uygundur ve TSE belgesine sahiptir.